DATA SHEET



POLYMERIC MACROFIBERS WITH GRAPHENE OXIDE

SECONDARY THREE-DIMENSIONAL REINFORCEMENT FOR CONCRETE



DATA SHEET POLYMERIC MACROFIBERS WITH GRAPHENE OXIDE

Description

Polyethylene and polypropylene macrofibers with Graphene Oxide (Graphenemex®) are used as secondary three- dimensional non structural reinforcement of concrete. Its nanotechnological formula provides high resistance macrofilaments and superior performance within the concrete than common fibers. Additionally, the macrofibers have been designed with mechanical retentions to maximize their anchorage and to increase their interfacial bond with the concrete to improve flexural strength.

Features

- Increases flexural strength in concrete,
- Improves the toughness, energy absorption and impact resistance of concrete,
- Reduces shrinkage cracking in fresh concrete,
- Reduces temperature cracks,
- Reduces segregation,
- Increases the mechanical strength and durability of concrete,
- Reduces the permeability of concrete,
- Does not corrode,
- Greater anti-spalling resistance in case of fire,
- High resistance to chemical attacks and alkalis,
- Reduces the cost per electrowelded mesh,
- Provides lint-free surfaces.
- Complies with ASTM C-1116 (Fiber Reinforced Concrete Specification) and ASTM C-1399 (Test to determine the average residual stress of fiber-reinforced

Use

As reinforcement of concrete subject to light, medium or heavy traffic; parking areas; canals and dams; elements cast with sliding formwork; wet or dry shotcrete, either permanent or temporary; precast elements.

Page 2 of 5



This document is the property of Energeia Fusion S.A. de C.V. Its partial or total reproduction is prohibited without prior authorization.

DATA SHEET

POLYMERIC MACROFIBERS WITH GRAPHENE OXIDE

Components and properties

Components	C	CAS No.	EC No.	%
Low- density polyethylene homopolymer	9002-88-4		-	> 75.0
Polypropylene homopolymer	9003-07-0		947-768-1	>10.0
Graphene oxide	7782-42-5		618-352-4	< 5.0
	Р	roperties	•	
Physical state: Solid	Ovidising n		roperties:	
Color: Gray		Not considered an oxidizing agent		
Odour: Odorless		Flammability (solid): 1		
Density: Not available		Moisture: 0%		
Specific gravity: 0.9		Alkali resistance: Excellent		
Dimensions: 47x1.5x2.0 mm		Solubility: Not soluble in water		
Denier: 8 DPF		Molecular Weight: Not available		
Shape (Design): crimped monofilament		pH: Not available		
Melting temperature: 50-170 °C		n-octanol/water partition coefficient: Not available		
Flash point: > 300 °C		Vapor pressure: Not available		
Decomposition temperature: Not available		Electrical Conductivity: Low		

Presentation

Pack of 10 individual bags with 4.8 lb (2.2 kg) each. Net content: 48.5 lb (22 kg) of macrofibers



Material handling

The dosing of the macrofibers into the mixer can be done during or after the mixing process. Equipment such as conveyor belts and dispensers can be used to add the macrofibers to the mixing hopper and/or stirring truck. Once incorporated, it is desirable to mix for 5 minutes at maximum speed until a homogeneous mixture and uniform distribution in the concrete is obtained.

Page 3 of 5

Dosage and performance:

A 4.8 lb (2.2 kg) bag has a yield for 1.3 yd^3 of concrete.



This document is the property of Energeia Fusion S.A. de C.V. Its partial or total reproduction is prohibited without prior authorization.

DATA SHEET POLYMERIC MACROFIBERS WITH GRAPHENE OXIDE

Recommendations

Prior to use, read the product data sheet and safety data sheet. The dosage of the macrofibers depends on the requirements of each project. It is responsibility of the user to carry out previous tests of the reinforced concrete before executing a large load to find the adequate dosage according to the tests and conditions of the specific work.

It is not recommended to increase the water content for the dispersion of the macrofibers, this would increase the contractions due to drying and there is a risk that cracks will appear, and the resistance of the concrete will decrease.

For concentrations above 5.06 lb/yd³ (3 kg/m³) in structural elements designed with ¹/₂" or larger rebar, fluidizing agents are recommended to ensure concrete flows through the reinforcement structures. This is because fibers in concrete can reduce fluidity and slump.

Safety precautions

The product in its current presentation is not classified as dangerous. Handle in accordance with conventional safety and hygiene practices at work. The use of gloves, boots, and safety glasses is recommended for handling macrofibers, especially when it is shotcrete.

Do not ingest.

Keep out of the reach of children.



Storage

The product should be stored in a dry place at room temperature, away from strong oxidizers and from sources of ignition. The standards and regulations in force in the place of application in terms of Hygiene, Safety and Environment must be complied.

Page 4 of 5



This document is the property of Energeia Fusion S.A. de C.V. Its partial or total reproduction is prohibited without prior authorization.

DATA SHEET POLYMERIC MACROFIBERS WITH GRAPHENE OXIDE

Waste management and environmental impact

The generation of waste should be avoided or minimized wherever may be possible. **Product:** Disposal of this product and any derivative must comply with the requirements of environmental protection and waste disposal legislation and all local authority requirements. The solid product is treated as waste material and can be disposed of as rubble or recycled.

Totally empty containers/packaging: can be treated as normal waste or recycled.

Expiration

Shelf life of 5 years in good storage conditions on its original package, indoors, in a cool and dry place, sunlight protected.

Legal note

The information contained in this data sheet is provided in good faith and is valid only for the product to which reference is made. The information is not intended to be exhaustive, and it is based on Energeia Fusion, S.A. de C.V. current knowledge, and experience, as long as the product is properly stored, handled and applied under normal conditions and in accordance with the recommendations expressed here. Due to the variability of materials, working conditions and purpose of use, the guarantee is limited solely to the quality of the product supplied. It is advisable to carry out the pertinent tests with the product to determine its suitability before its final application.

In case of changes in parameters of application or if it is planned to use for a different application, consult Technical Service.

Energeia Fusion, S.A. de C.V. is not responsible for any damage that may be caused by misuse of the product.

For more information contact contact@graphenemex.com.

(Code	I-ENER-8.3
	Version	1
C	Revision	01-05-2025



Page 5 of 5